

Topolymer[®] 5313-801B

Halogen Free Flame Retardant Thermoplastic Elastomer

Product Description

Topolymer[®] 5313-801B is a halogen free flame retardant thermoplastic elastomer compound based on SEBS/PP. This material can be widely used in USB cable, Sealing strip, etc. This grade is designed for extrusion. It is completely recyclable.

General

Appearance √Black Color

Feature √Flame Retardant V0 √Rating Temperature 90°C √UL Yellow Card

√Crack Resistance √Wear Resistance √Fasy Processing

 $\begin{array}{ccc} & & & & & & \\ \sqrt{\text{Weather Resistance}} & & & \sqrt{\text{Easy Processing}} \\ \text{Compliance} & & & \sqrt{\text{ROHS}} & & \sqrt{\text{REACH}} \end{array}$

Form √Pellet Packaging √25kg/bag

Technical Property

Typical Properties	Typical Value	Unit	Test Method
Hardness	80	Shore A	ASTM D-2240
Density	1.04	g/cm ³	ASTM D-792
Tensile Strength at break	11	MPa	ASTM D-412
Tensile Strength at 100%	4.0	MPa	ASTM D-412
Elongation at Break	500	%	ASTM D-412
Tearing Strength	10	KN/m	ASTM D624
Rating Temperature	90	℃	UL1581
Flame Retardant	Pass	V0	UL94

The data are not to be defined as specifications

Processing Information

Extrusion	Typical Value	
Melt Temp	190-220℃	
Rear Temperature	160-180℃	
Middle Temperature	190-220℃	
Front Temperature	190-220℃	
Head Temperature	160-200℃	
Die Temperature	160-200℃	
Filter	100 -150 mesh	
Compress Ratio	2.8:1	

Notes:

- This product is incompatible with PVC, Purge thoroughly before and after use of this product with a low flow (0.5 2.5 MFR)
 Polyethylene (PE) or Polypropylene (PP).
- 2) The product needs to be dried for 2-3 hours at 90 °C before use
- 3) In good ventilation, the product can be stored for six months from the date of production. Property check is required if the storage time is over 6 months.

Contact Information

Top Polymer Enterprise Ltd tpe@topolymer.com www.topolymer.com

10 Xiyuan Rd, Tianmuhu Industrial Park Liyang, Jiangsu China

Tel: +86 (519) 8796 6118 Fax: +86 (519) 8796 6228 Zhen An Hi-tech Park, Chang An, Dongguan, Guangdong China

Tel: +86 (769) 8584 6000 Fax: +86 (769) 8584 6001

All information supplied by or on behalf of Top Polymer in relation to its products, whether in nature of data, recommendations or otherwise, is supported by research and believed reliable, but Top Polymer assumes no liability whatever in respect of application, processing or use made of the mentioned information or products, or any consequence. The buyer shall undertake all liability in respect of the application, processing or use of the mentioned information or products, or any consequence.

Rev.2016-05-30