

Topolymer® 3211-551B

Styrenic Thermoplastic Elastomer

Product Description

Topolymer® 3211-551B is a TPE compound based on Styrenic Block Copolymer (SBC). This material can be widely used in communication cable, earphone cord, USB cable, sealing strip, etc. This grade is designed for extrusion, and can be co-extruded with PP. It is completely recyclable.

General

Appearance √Black Color

Feature VSoft Touch VTear Resistance VKink Resistance

Form $\sqrt{\text{Pellet}}$ Packaging $\sqrt{25\text{kg/bag}}$

Technical Property

Typical Properties	Typical Value	Unit	Test Method
Hardness	53	Shore A	ASTM D-2240
Density	0.92	g/cm ³	ASTM D-792
Tensile Strength at break	6.5	MPa	ASTM D-412
Tensile Strength at 100%	1.4	MPa	ASTM D-412
Elongation at Break	750	%	ASTM D-412
Tear Strength	24	KN/m	ASTM D624
Compression Set at 23°C x 22hr	15	%	ASTM D395B

The data are not to be defined as specifications

Processing Information

Extrusion	Typical Value	
Melt Temp	170-200°C	
Rear Temperature	140-160°C	
Middle Temperature	160-180°C	
Front Temperature	160-190°C	
Head Temperature	160-190°C	
Die Temperature	140-220°C	
Filter	100 -150 mesh	
Compress Ratio	3:1	

Notes:

Contact Information

Top Polymer Enterprise Ltd tpe@topolymer.com www.topolymer.com

10 Xiyuan Rd, Tianmuhu Industrial Park Liyang, Jiangsu China

Tel: +86 (519) 8796 6118 Fax: +86 (519) 8796 6228 Zhen An Hi-tech Park, Chang An, Dongguan, Guangdong China

Tel: +86 (769) 8584 6000 Fax: +86 (769) 8584 6001

All information supplied by or on behalf of Top Polymer in relation to its products, whether in nature of data, recommendations or otherwise, is supported by research and believed reliable, but Top Polymer assumes no liability whatever in respect of application, processing or use made of the mentioned information or products, or any consequence. The buyer shall undertake all liability in respect of the application, processing or use of the mentioned information or products, or any consequence.

Rev.2016-05-30

¹⁾ The product is incompatible with PVC. Purge thoroughly before and after use of this product with a low flow (0.5 - 2.5 MFR) Polyethylene (PE) or Polypropylene (PP).

²⁾ Drying is not required. However, if moisture is a problem or to get better appearance, dry pellets for 3 hours at 60°C