



# Topolymer® 8228-601N

## Styrenic Thermoplastic Elastomer

### Product Description

Topolymer® 8228-601N is a TPE compound based on Styrenic Block Copolymer (SBC). This material can be over-molded onto PA6/PA66 or used for single molding. This grade is designed for injection molding. It is completely recyclable.

### General

Appearance	√Natural color		
Feature	√Soft Touch	√Easy Coloring	√Tear Resistance
Compliance	√RoHS	√REACH	√FDA
Form	√Pellet		
Packaging	√25kg/bag		

### Technical Property

Typical Properties	Typical Value	Unit	Test Method
Hardness	62	Shore A	ASTM D2240
Density	1.12	g/cm <sup>3</sup>	ASTM D792
Tensile Strength at break	2.4	MPa	ASTM D412
Tensile Strength at 100%	1.9	MPa	ASTM D412
Elongation at Break	300	%	ASTM D412
Tear Strength	16	KN/m	ASTM D624
Compression Set at 23°C x 22hr	16	%	ASTM D395B

The data are not to be defined as specifications.

**Processing Information**

<b>Injection</b>	<b>Typical Value</b>
Rear Temperature	180-220°C
Middle Temperature	210-260°C
Front Temperature	220-270°C
Nozzle Temperature	220-270°C
Mold Temperature	25-80°C
Injection Rate	Fast/Medium
Back Pressure	0.35-0.7MPa
Screw Speed	30-80rpm
Screw L/D Ratio	22:1
Screw Compression Ratio	2:1-4:1

Notes:

- 1) The product is incompatible with PVC. Purge thoroughly before and after use of this product with a low flow (0.5 - 2.5 MFR) Polyethylene (PE) or Polypropylene (PP).
- 2) Color concentrate with PP, LDPE or EVA based carrier is recommended.
- 3) The product needs to be dry before use, dry pellets for 2 hours at 70°C.

**Contact Information**

Top Polymer Enterprise Ltd  
 tpe@topolymer.com  
 www.topolymer.com

10 Xiyuan Rd, Tianmuhu Industrial Park  
 Liyang, Jiangsu  
 China  
 Tel: +86 (519) 8796 6118  
 Fax: +86 (519) 8796 6228

Zhen An Hi-tech Park,  
 Chang An, Dongguan, Guangdong  
 China  
 Tel: +86 (769) 8584 6000  
 Fax: +86 (769) 8584 6001

All information supplied by or on behalf of Top Polymer in relation to its products, whether in nature of data, recommendations or otherwise, is supported by research and believed reliable, but Top Polymer assumes no liability whatever in respect of application, processing or use made of the mentioned information or products, or any consequence. The buyer shall undertake all liability in respect of the application, processing or use of the mentioned information or products, or any consequence.  
 Rev.2016-05-30