



# Topthane™ 2170

## Urethane Thermoplastic Elastomer

### Product Description

Topthane™ 2170 is a polyester-based Urethane Thermoplastic Elastomer resin in the family of Thermoplastic Elastomer (TPE). The product can be widely used in automotive accessories, protective cases, electronics, sports gear, seals, shoe parts and other applications where flexibility is needed. This grade is designed for injection molding. It is completely recyclable.

### General

Appearance	√Clear		
Feature	√Low Temperature Flexibility	√Abrasion Resistance	√Tear Resistance
	√Oil And Chemical Resistance	√Easy Processing	
Compliance	√RoHS	√REACH	
Form	√Pellet		
Packaging	√25kg/bag		

### Technical Property

Typical Properties	Typical Value	Unit	Test Method
Hardness	70	Shore A	ASTM D2240
Density	1.16	g/cm <sup>3</sup>	ASTM D792
Tensile Strength at break	25.5	MPa	ASTM D412
Tensile Strength at 100%	2.6	MPa	ASTM D412
Tensile Strength at 300%	4.6	MPa	ASTM D412
Elongation at Break	800	%	ASTM D412
Tear Strength	61.2	KN/m	ASTM D624

The data are not to be defined as specifications.

## Processing Information

Injection	Typical Value
Rear Temperature	170-180°C
Middle Temperature	180-200°C
Front Temperature	190-210°C
Nozzle Temperature	195-205°C
Screw Speed	50-80rpm
Back Pressure	0.3-0.6MPa
Injection Pressure	50-100MPa
Holding Pressure	30-60MPa
Injection Rate	Slow

**Notes:**

- 1) The product is incompatible with PVC. Purge thoroughly before and after use of this product with a low flow (0.5 - 2.5 MFR) Polyethylene (PE) or Polypropylene (PP).
- 2) Color concentrate with TPU based carrier is recommended.
- 3) The product needs to be dry before use, dry pellets for 3-4 hours at 90-110°C.

## Contact Information

Top Polymer Enterprise Ltd  
 tpe@topolymer.com  
 www.topolymer.com

10 Xiyuan Rd, Tianmu Industrial Park  
 Liyang, Jiangsu  
 China  
 Tel: +86 (519) 8796 6118  
 Fax: +86 (519) 8796 6228

Zhen An Hi-tech Park,  
 Chang An, Dongguan, Guangdong  
 China  
 Tel: +86 (769) 8584 6000  
 Fax: +86 (769) 8584 6001

All information supplied by or on behalf of Top Polymer in relation to its products, whether in nature of data, recommendations or otherwise, is supported by research and believed reliable, but Top Polymer assumes no liability whatever in respect of application, processing or use made of the mentioned information or products, or any consequence. The buyer shall undertake all liability in respect of the application, processing or use of the mentioned information or products, or any consequence.  
 Rev.2016-05-30