

# Topthane<sup>™</sup> 2185

## **Urethane Thermoplastic Elastomer**

## **Product Description**

Topthane<sup>™</sup> 2185 is a polyester-based Urethane Thermoplastic Elastomer resin in the family of Thermoplastic Elastomer (TPE). The product can be widely used in automotive accessories, protective cases, electronics, sports gear, seals, shoe parts and other applications where flexibility is needed. This grade is designed for injection molding. It is completely recyclable.

### General

Packaging

Appearance √Clear

Feature √Low Temperature Flexibility √Abrasion Resistance √Tear Resistance

√Oil And Chemical Resistance √Easy Processing

Compliance  $\sqrt{\text{RoHS}}$   $\sqrt{\text{REACH}}$  Form  $\sqrt{\text{Pellet}}$ 

√25kg/bag

## **Technical Property**

Typical Properties	Typical Value	Unit	Test Method
Hardness	85	Shore A	ASTM D2240
Density	1.18	g/cm <sup>3</sup>	ASTM D792
Tensile Strength at break	39.8	MPa	ASTM D412
Tensile Strength at 100%	8.16	MPa	ASTM D412
Tensile Strength at 300%	16.3	MPa	ASTM D412
Elongation at Break	700	%	ASTM D412
Tear Strength	91.8	KN/m	ASTM D624

The data are not to be defined as specifications.

## Topthane™ 2185

## **Product Data Sheet**

## **Processing Information**

Injection	Typical Value
Rear Temperature	170-180℃
Middle Temperature	180-200℃
Front Temperature	190-210℃
Nozzle Temperature	200-210℃
Screw Speed	50-80rpm
Back Pressure	0.3-0.6MPa
Injection Pressure	50-100MPa
Holding Pressure	30-60MPa
Injection Rate	Slow

#### Notes

- 1) The product is incompatible with PVC. Purge thoroughly before and after use of this product with a low flow (0.5 2.5 MFR) Polyethylene (PE) or Polypropylene (PP).
- 2) Color concentrate with TPU based carrier is recommended.
- 3) The product needs to be dry before use, dry pellets for 3-4 hours at 90-110°C.

### **Contact Information**

Top Polymer Enterprise Ltd tpe@topolymer.com www.topolymer.com

10 Xiyuan Rd, Tianmuhu Industrial Park Liyang, Jiangsu China

Tel: +86 (519) 8796 6118 Fax: +86 (519) 8796 6228 Zhen An Hi-tech Park, Chang An, Dongguan, Guangdong China

Tel: +86 (769) 8584 6000 Fax: +86 (769) 8584 6001