



Topthane™ 2195E

Urethane Thermoplastic Elastomer

Product Description

Topthane™ 2195E is a polyester-based Urethane Thermoplastic Elastomer resin in the family of Thermoplastic Elastomer (TPE). The product can be widely used in pipe, wire and cable, conveyor belt, sports gear, electronics, polymer modification, etc. This grade is designed for Extrusion. It is completely recyclable.

General

Appearance	√Clear		
Feature	√Low Temperature Flexibility	√Abrasion Resistance	√Tear Resistance
	√Oil And Chemical Resistance	√Extrusion Stability	
Compliance	√RoHS	√REACH	
Form	√Pellet		
Packaging	√25kg/bag		

Technical Property

Typical Properties	Typical Value	Unit	Test Method
Hardness	95	Shore A	ASTM D2240
Density	1.19	g/cm ³	ASTM D792
Tensile Strength at break	34.7	MPa	ASTM D412
Tensile Strength at 100%	11.2	MPa	ASTM D412
Tensile Strength at 300%	17.3	MPa	ASTM D412
Elongation at Break	450	%	ASTM D412
Tear Strength	112.2	KN/m	ASTM D624

The data are not to be defined as specifications.

Processing Information

Extrusion	Typical Value
Rear Temperature	180-190°C
Middle Temperature	190-210°C
Front Temperature	200-220°C
Die Temperature	200-210°C
Recommended Filter Mesh	80/120/80 mesh
Screw Rotation Rate	20-40 rpm

Notes:

- 1) The product is incompatible with PVC. Purge thoroughly before and after use of this product with a low flow (0.5 - 2.5 MFR) Polyethylene (PE) or Polypropylene (PP).
- 2) Color concentrate with TPU based carrier is recommended.
- 3) The product needs to be dry before use, dry pellets for 3-4 hours at 90-110°C.

Contact Information

Top Polymer Enterprise Ltd
tpe@topolymer.com
www.topolymer.com

10 Xiyuan Rd, Tianmu Industrial Park
Liyang, Jiangsu
China
Tel: +86 (519) 8796 6118
Fax: +86 (519) 8796 6228

Zhen An Hi-tech Park,
Chang An, Dongguan, Guangdong
China
Tel: +86 (769) 8584 6000
Fax: +86 (769) 8584 6001

All information supplied by or on behalf of Top Polymer in relation to its products, whether in nature of data, recommendations or otherwise, is supported by research and believed reliable, but Top Polymer assumes no liability whatever in respect of application, processing or use made of the mentioned information or products, or any consequence. The buyer shall undertake all liability in respect of the application, processing or use of the mentioned information or products, or any consequence.

Rev.2016-05-30