



Topester™ 472RM

Copolyester Thermoplastic Elastomer

Product Description

Topester™ 472RM is a Copolyester Thermoplastic Elastomer (TPC) resin in the family of Thermoplastic Elastomer (TPE). This material can be widely used in automotive, industrial, wire & cable, consumer, polymer modification, etc. This grade is designed for extrusion and injection molding. It is completely recyclable.

General

| | | |
|------------|------------------|------------------|
| Appearance | √Natural Color | |
| Feature | √Heat Resistance | √Good Resilience |
| Compliance | √RoHS | √REACH |
| Form | √Pellet | |
| Packaging | √25kg/bag | |

Technical Property

| Typical Properties | Typical Value | Unit | Test Method |
|---|---------------|-------------------|-------------|
| Hardness | 72 | Shore D | ISO 868 |
| Density | 1.26 | g/cm ³ | ISO 1183 |
| Melt Index (230°C x 2.16kg) | 13 | g/10min | ISO 1133 |
| Flexural Modulus | 550 | MPa | ISO 178 |
| Tensile Stress at break | 42 | MPa | ISO 527 |
| Elongation at Break | 370 | % | ISO 527 |
| Charpy Notched Impact Strength at 23°C | 15 | KJ/m ² | ISO 179 |
| Charpy Notched Impact Strength at -30°C | 9 | KJ/m ² | ISO 179 |
| Melting Temperature | 219 | °C | ISO11357 |
| Vicat Softening Temperature, 10N | 205 | °C | ISO 306 |
| Volume Resistivity | 1.0E+14 | Ohm*cm | IEEC 60093 |
| Water Absorption, 24hr | 0.3 | % | ISO 62 |
| Shrinkage | 1.7 | % | ISO 294 |

The data are not to be defined as specifications

Processing Information

| Extrusion | Typical Value |
|--------------------------|----------------------|
| Rear Temperature | 180-220°C |
| Middle Temperature | 220-250°C |
| Front Temperature | 220-250°C |
| Head Temperature | 220-250°C |
| Die Temperature | 220-250°C |
| Injection Molding | Typical Value |
| Rear Temperature | 180-220°C |
| Middle Temperature | 220-250°C |
| Front Temperature | 220-250°C |
| Nozzle Temperature | 220-250°C |
| Mold Temperature | 20-60°C |

Notes:

- 1) The product is incompatible with PVC. Purge thoroughly before and after use of this product with a low flow (0.5 - 2.5 MFR) Polyethylene (PE) or Polypropylene (PP).
- 2) Color concentrate with Copolyester based carrier is recommended.
- 3) Drying is required for 3-5 hours at 110°C

Contact Information

Top Polymer Enterprise Ltd
tpe@topolymer.com
www.topolymer.com

10 Xiyuan Rd, Tianmuhu Industrial Park
Liyang, Jiangsu
China
Tel: +86 (519) 8796 6118
Fax: +86 (519) 8796 6228

Zhen An Hi-tech Park,
Chang An, Dongguan, Guangdong
China
Tel: +86 (769) 8584 6000
Fax: +86 (769) 8584 6001

All information supplied by or on behalf of Top Polymer in relation to its products, whether in nature of data, recommendations or otherwise, is supported by research and believed reliable, but Top Polymer assumes no liability whatever in respect of application, processing or use made of the mentioned information or products, or any consequence. The buyer shall undertake all liability in respect of the application, processing or use of the mentioned information or products, or any consequence.
Rev.2016-05-30