



Topolymer® 9310-551B

Thermoplastic Vulcanizate

Product Description

Topolymer® 9310-551B is a heat-stabilized PP/EPDM based Thermoplastic Vulcanizate (TPV) in the family of Thermoplastic Elastomer (TPE). This material is designed for a wide range of applications such as automotive interiors and exteriors, construction seals, gaskets, electricals, consumer products or other parts where softness and conformity are needed. This grade can be processed on conventional thermoplastics processing equipments for Injection Molding, Extrusion and Blow Molding or other hot melt processes. It is completely recyclable.

General

Appearance	✓ Black Color		
Feature	✓ Non-hygroscopic	✓ Low VOC	✓ Easy Processing
	✓ High Resilience	✓ Enhanced UV resistance	✓ Smooth Surface
Compliance	✓ RoHS	✓ REACH	
Form	✓ Pellet		
Packaging	✓ 25kg/bag		

Technical Property

Typical Properties	Typical Value	Unit	Test Method
Hardness	56	Shore A	ASTM D2240
Density	0.96	g/cm ³	ASTM D792
Tensile Strength at break	4.9	MPa	ASTM D412
Tensile Strength at 100%	2.2	MPa	ASTM D412
Elongation at Break	430	%	ASTM D412
Tear Strength - Across Flow	24	KN/m	ASTM D624
Compression Set 70°Cx22h	34	%	ASTM D395B
Brittleness Temperature	-60	°C	ASTM D746
Change in Tensile Strength In Air 150°Cx168h	-13	%	ASTM D573
Change in Ultimate Elongation In Air 150°Cx168h	-10	%	ASTM D573
Change in Durometer Hardness in Air 150°Cx168h	+3	Shore A	ASTM D2240

The data are not to be defined as specifications

Processing Information

Injection	Typical Value
Suggested Max Moisture	0.08%
Suggested Max Regrind	20%
Rear Temperature	175-190°C
Middle Temperature	180-195°C
Front Temperature	185-200°C
Nozzle Temperature	185-210°C
Mold Temperature	25-55°C
Injection Rate	Fast
Back Pressure	0.35-0.7MPa
Screw Speed	100-200rpm
Clamp Tonnage	40-70MPa
Screw L/D Ratio	16:1-24:1
Screw Compression Ratio	2:1-4:1
Extrusion	Typical Value
Melt Temperature	175-215°C
Die Temperature	175-215°C

Notes:

- 1) Topolymer® TPV is incompatible with PVC, Purge thoroughly before and after use of this product with a low flow (0.5 - 2.5 MFR) Polyethylene (PE) or Polypropylene (PP).
- 2) Drying is not required. However, if moisture is a problem or to get better appearance, dry pellets for 3 hours at 80°C

Contact Information

Top Polymer (China)
 tpe@topolymer.com
 www.topolymer.com

10 Xiyuan Rd, Tianmuhu Industrial Park
 Liyang, Jiangsu
 China
 Tel: +86 (519) 8796 6118
 Fax: +86 (519) 8796 6228

1017 Building 1, No. 1 Junma Street, Chigang
 Humen Town, Dongguan City, GuangDong
 China
 Tel: +86 (769) 8584 6000
 Fax: +86 (769) 8584 6001

All information supplied by or on behalf of Top Polymer in relation to its products, whether in nature of data, recommendations or otherwise, is supported by research and believed reliable, but Top Polymer assumes no liability whatever in respect of application, processing or use made of the mentioned information or products, or any consequence. The buyer shall undertake all liability in respect of the application, processing or use of the mentioned information or products, or any consequence.

Rev.2024-01-01