



Topolymer[®] RCC 8232-651N

Styrenic Thermoplastic Elastomer

Product Description

Topolymer[®] RCC 8232-651N is a TPE compound based on Styrenic Block Copolymer (SBC). This material can be over-molded onto PP or used for single injection. This grade contains 25% PCR material , which is 100% recyclable.

General

Appearance	✓ Natural		
Feature	✓ Soft Touch	✓ Silky Feel	✓ Easy Coloring
	✓ Tear Resistance		
Compliance	✓ RoHS	✓ REACH	✓ FDA
Form	✓ Pellet		
Packaging	✓ 25kg/bag		

Technical Property

Typical Properties	Typical Value	Unit	Test Method
Hardness	65	Shore A	ASTM D2240
Density	0.89	g/cm ³	ASTM D792
Tensile Strength at break	6.5	MPa	ASTM D412
Elongation at Break	700	%	ASTM D412
Tear Strength	28	KN/m	ASTM D624

The data are not to be defined as specifications.

Processing Information

Injection	Typical Value
Rear Temperature	170-180°C
Middle Temperature	180-220°C
Front Temperature	180-220°C
Nozzle Temperature	190-230°C
Mold Temperature	20-40°C
Injection Rate	Fast/Medium
Back Pressure	0.35-0.7MPa
Screw Speed	30-80rpm
Screw L/D Ratio	22:1
Screw Compression Ratio	2:1-4:1

Notes:

- 1) The product is incompatible with PVC. Purge thoroughly before and after use of this product with a low flow (0.5 - 2.5 MFR) Polyethylene (PE) or Polypropylene (PP).
- 2) Color concentrate with PP, LDPE or EVA based carrier is recommended.
- 3) Drying is not required. However, if moisture is a problem or to get better appearance, dry pellets for 3 hours at 60°C.

Contact Information

Top Polymer (China)
tpe@topolymer.com
www.topolymer.com

10 Xiyuan Rd, Tianmuhu Industrial Park
Liyang, Jiangsu
China
Tel: +86 (519) 8796 6118
Fax: +86 (519) 8796 6228

1017 Building 1, No. 1 Junma Street, Chigang
Humen Town, Dongguan City, Guangdong
China
Tel: +86 (769) 8584 6000
Fax: +86 (769) 8584 6001

All information supplied by or on behalf of Top Polymer in relation to its products, whether in nature of data, recommendations or otherwise, is supported by research and believed reliable, but Top Polymer assumes no liability whatever in respect of application, processing or use made of the mentioned information or products, or any consequence. The buyer shall undertake all liability in respect of the application, processing or use of the mentioned information or products, or any consequence.

Rev.2024-01-01