

Topolymer[®] ECO 5732-801G

Halogen Free Flame Retardant Thermoplastic Elastomer

Product Description

Topolymer[®] ECO 5732-801G is a halogen free flame retardant thermoplastic elastomer compound based on SEBS/PP. The Bio-based carbon content is 15%. This material can be widely used in power plug, electronic & electrical, automotive, etc. This grade is designed for injection molding. It is completely recyclable.

General

√ Grey Color
√ Soft Touch
\checkmark Bend Resistance
√ RoHS
√ Pellet
√25kg/bag

√ Tear Resistance
√ Heat Resistance
√ REACH

√ UL Yellow Card √ Weather Resistance

Technical Property

Typical Properties	Typical Value	Unit	Test Method
Hardness	86	Shore A	ASTM D-2240
Density	1.06	g/cm³	ASTM D-792
Tensile Strength at break	7.4	MPa	ASTM D-412
Tensile Strength at 100%	4.2	MPa	ASTM D-412
Elongation at Break	566	%	ASTM D-412
Tearing Strength	13.3	KN/m	ASTM D624
Rating Temperature	80	°C	UL1581
Flame Retardant	Pass	VO	UL94

The data are not to be defined as specifications

Topolymer[®] ECO 5732-801G

Processing Information

Injection	Typical Value
Rear Temperature	160-180℃
Middle Temperature	180-210°C
Front Temperature	180-210°C
Nozzle Temperature	160-90°C
Mold Temperature	40-60°C
Injection Rate	Fast
Back Pressure	0.35-0.7MPa
Screw Speed	100-200rpm
Clamp Tonnage	40-70MPa
Screw L/D Ratio	16:1-24:1
Screw Compression Ratio	2:1-4:1

Notes:

1) The product is incompatible with PVC, Purge thoroughly before and after use of this product with a low flow (0.5 - 2.5 MFR) Polyethylene (PE) or Polypropylene (PP).

2) The product needs to be dried for 2-3 hours at 90°C before use

3) In good ventilation, the product can be stored for six months from the date of production. Property check is required if storage time is over 6 months

Contact Information

Top Polymer Enterprise Ltd tpe@topolymer.com www.topolymer.com

10 Xiyuan Rd, Tianmuhu Industrial Park Liyang, Jiangsu China Tel: +86 (519) 8796 6118 Fax: +86 (519) 8796 6228 1017 Building 1, No. 1 Junma Street, Chigang Humen Town, Dongguan City, GuangDong China Tel: +86 (769) 8584 6000 Fax: +86 (769) 8584 6001

All information supplied by or on behalf of Top Polymer in relation to its products, whether in nature of data, recommendations or otherwise, is supported by research and believed reliable, but Top Polymer assumes no liability whatever in respect of application, processing or use made of the mentioned information or products, or any consequence. The buyer shall undertake all liability in respect of the application, processing or use of the mentioned information or products, or any consequence. Rev.2024-01-01