



# Topolymer<sup>®</sup> ECO 5732-901W

## Halogen Free Flame Retardant Thermoplastic Elastomer

### Product Description

Topolymer<sup>®</sup> ECO 5732-901W is a halogen free flame retardant thermoplastic elastomer compound based on SEBS/PP. The Bio-based carbon content is 20%. This material can be widely used in power plug, electronic & electrical, automotive, etc. This grade is designed for injection molding. It is completely recyclable

### General

Appearance	✓ White Color		
Feature	✓ Soft Touch	✓ Tear Resistance	✓ UL Yellow Card
	✓ Bend Resistance	✓ Heat Resistance	✓ Weather Resistance
Compliance	✓ RoHS	✓ REACH	
Form	✓ Pellet		
Packaging	✓ 25kg/bag		

### Technical Property

Typical Properties	Typical Value	Unit	Test Method
Hardness	90	Shore A	ASTM D-2240
Density	1.04	g/cm <sup>3</sup>	ASTM D-792
Tensile Strength at break	9	MPa	ASTM D-412
Tensile Strength at 100%	6.9	MPa	ASTM D-412
Elongation at Break	447	%	ASTM D-412
Tearing Strength	17.3	KN/m	ASTM D624
Rating Temperature	80	°C	UL1581

Flame Retardant	Pass	V0	UL94
-----------------	------	----	------

The data are not to be defined as specifications

### Processing Information

Injection	Typical Value
Rear Temperature	160-180°C
Middle Temperature	180-210°C
Front Temperature	180-210°C
Nozzle Temperature	160-90°C
Mold Temperature	40-60°C
Injection Rate	Fast
Back Pressure	0.35-0.7MPa
Screw Speed	100-200rpm
Clamp Tonnage	40-70MPa
Screw L/D Ratio	16:1-24:1
Screw Compression Ratio	2:1-4:1

Notes:

- 1) The product is incompatible with PVC, Purge thoroughly before and after use of this product with a low flow (0.5 - 2.5 MFR) Polyethylene (PE) or Polypropylene (PP).
- 2) The product needs to be dry before use, dry pellets for 2-3 hours at 90°C
- 3) In good ventilation, the product can be stored for six months from the date of production. Property check is required if storage time is over 6 months

### Contact Information

Top Polymer Enterprise Ltd  
 tpe@topolymer.com  
 www.topolymer.com

10 Xiyuan Rd, Tianmuhu Industrial Park  
 Liyang, Jiangsu  
 China  
 Tel: +86 (519) 8796 6118  
 Fax: +86 (519) 8796 6228

1017 Building 1, No. 1 Junma Street, Chigang  
 Humen Town, Dongguan City, Guangdong  
 China  
 Tel: +86 (769) 8584 6000  
 Fax: +86 (769) 8584 6001

All information supplied by or on behalf of Top Polymer in relation to its products, whether in nature of data, recommendations or otherwise, is supported by research and believed reliable, but Top Polymer assumes no liability whatever in respect of application, processing or use made of the mentioned

information or products, or any consequence. The buyer shall undertake all liability in respect of the application, processing or use of the mentioned information or products, or any consequence.

Rev.2024-01-01