



Topliner[®] 8766H

Styrenic thermoplastic elastomer

Product Description

Topliner[®] 8766H is a Styrenic Thermoplastic Elastomer resin in the family of Thermoplastic Elastomer (TPE). The product can be widely used in pull ring caps, anti-theft cap inner pads, suitable for pasteurization filling bottle cap inner pads. This grade is designed for Extrusion. It is completely recyclable.

General

- Appearance ✓ Translucent
- Feature ✓ Excellent sealing performance ✓ Steam sterilization ✓ Low odor
- ✓ high-efficiency squash oxygen
- Compliance ✓ RoHS ✓ GB 21928 ✓ FDA
- Form ✓ Pellet
- Packaging ✓ 25kg/bag

Technical Property

Typical Properties	Typical Value	Unit	Test Method
Hardness	40	Shore A	ASTM D-2240
Density	0.92	g/cm ³	ASTM D-792
Tensile Strength	11	MPa	ASTM D-412
Elongation at Break	720	%	ASTM D-412
Tear Strength	60	KN/m	ASTM D624

The data are not to be defined as specifications.

Processing Information

Drop-molding/Extrusion	Typical Value
Rear Temperature Middle Temperature Front Temperature Head Temperature	100°C-120°C 110°C-120°C 110°C-130°C 120°C-250°C
Filter	100 -150 mesh
Compress Ratio	3:1

Notes:

- 1) The product is incompatible with PVC. Purge thoroughly before and after use of this product with a low flow (0.5 - 2.5 MFR) Polyethylene (PE) or Polypropylene (PP).
- 2) Use the product as soon as possible after opening the package.

Contact Information

Top Polymer Enterprise Ltd
tpe@topolymer.com
www.topolymer.com

10 Xiyuan Rd, Tianmuhu Industrial Park
Liyang, Jiangsu
China
Tel: +86 (519) 8796 6118
Fax: +86 (519) 8796 6228

1017 Building 1, No. 1 Junma Street, Chigang
Humen Town, Dongguan City, Guangdong
China
Tel: +86 (769) 8584 6000
Fax: +86 (769) 8584 6001

All information supplied by or on behalf of Top Polymer in relation to its products, whether in nature of data, recommendations or otherwise, is supported by research and believed reliable, but Top Polymer assumes no liability whatever in respect of application, processing or use made of the mentioned information or products, or any consequence. The buyer shall undertake all liability in respect of the application, processing or use of the mentioned information or products, or any consequence.

Rev.2024-01-01